

HARDNESS OF THE WOOD

SPECIES	Load required to Enter a sphere of 0.444 in diam species until mi-diameter (lb)*
FEUILLUS	
Hickory	2138 lbs
Sugar Maple	1638 lbs
White Oak	1602 lbs
White Ash	1586 lbs
Bambou (For information only)	1520 lbs
Red Oak	1388 lbs
Slippery Elm	1378 lbs
Yellow Birch	1332 lbs
Black Walnut	1180 lbs
Cherry	990 lbs
Red Maple (Plain)	984 lbs
Birch (White birch)	972 lbs
Silver Maple	850 lbs
Poplar Largetooth	415 lbs
RESINOUS	
Castor Larch (larch)	724 lbs
Douglas-fir (Douglas fir from the West)	672 lbs
Red Pine	476 lbs
White Pine	372 lbs
Western Red Cedar	331 lbs

* Forintek Canada Corp. (Resistance and Related Properties of Woods Grown in Canada)